

Effectiveness of FRP in Reducing Corrosion in a Marine Environment



Rajan Sen, Gray Mullins and Danny Winters

Department of Civil & Environmental Engineering
USF, Tampa FL

K S Suh

PB Americas, Inc.
Tampa FL

**2009 US Army Corrosion Summit
Clearwater, FL**

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE FEB 2009		2. REPORT TYPE		3. DATES COVERED 00-00-2009 to 00-00-2009	
4. TITLE AND SUBTITLE Effectiveness of FRP in Reducing Corrosion in a Marine Environment				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of South Florida ,Department of Civil & Environmental Engineering,4202 E. Fowler Ave,Tampa,FL, 33620				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES 2009 U.S. Army Corrosion Summit, 3-5 Feb, Clearwater Beach, FL					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 37	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Pile Corrosion



Pile Corrosion



Courtesy - Alltrista





Outline




- Background
- Test Program
- Findings
- Field Applications
- Concluding Remarks
- Acknowledgements

Project Goals




- How effective is FRP in mitigating corrosion?
- How important is the pre-wrap repair?
(Not covered)
- How feasible is it to conduct field repairs?

Tuutti's Corrosion Model



Test Specimen





ATR Reference Electrode

Thermocouple

Thermocouple

Reference Electrode





Concrete + chlorides

FRP Wrapping



- 28 days
- Glass
 - 1, 2, 3, 4 layers
- Carbon
 - 1, 2, 3, 4 layers

Carbon Fiber Wrap



Glass Fiber Wrap



Ambient Exposure



Outdoors

- 3.5% salt water
- Wet/dry cycles: every 6 hrs
- 1160 days (3 yrs 2 months)




Indoor


Controls vs Wrapped Specimens




Effect on Corrosion Rate





Role of Layers - CFRP




Role of Layers - GFRP



Unwrapped Controls



Wrapped Specimens



Retrieved Strands



Outdoor Control


30 wire
breaks in
6 controls




CFRP Wrapped

1 wire
break in
16 FRP
specimen

1/3rd Metal Loss in Wrapped Specimens




Implications



Why?




- Tests are underway to evaluate FRP's performance as a barrier
- If possible, we would like to evaluate coatings that could conceivably be used to improve FRP's performance



NSF Funded
Study

Field Validation

Field Demonstration Studies




Allen Creek Bridge, Clearwater



Friendship Trails Bridge


Gandy Bridge



Gandy Bridge, Tampa



Linear
Polarization



Junction Box
Installation

Measured Corrosion Rates in Controls vs Wrapped Piles

Pile	Date	Rate ($\mu\text{m}/\text{yr}$)
Control 91 cm above HWL	Nov 2004	8.39
	Jun 2005	6.77
	Aug 2007	9.46
Control 31 cm Below HWL	Nov 2004	49.6
	Jun 2005	20.48
	Aug 2007	38.48
Wrapped Pile 91 cm above HWL	Nov 2004	18.52
	Jun 2005	7.34
	July 2007	5.75
Wrapped Pile 31 cm Below HWL	Nov 2004	194.09
	Jun 2005	38.82
	July 2007	10.19


Latest Application

Grove Isle Bridge, Miami

January 2009







CP + Wrap + Pressure Bag



NCHRP-IDEA-128

Concluding Remarks

- 😊 FRP slows down the corrosion rate
- 😊 Performance of CFRP and GFRP are comparable
- 😊 Performance appears to be independent of number of layers
- 😊 Linear polarization correctly predicts trends

Acknowledgements



- Inam Jawed, NCHRP-IDEA
- Michael Sprinkel, VTRC
- Nils Olsson, Hillsborough County
- Prof. A. Sagues, USF
- National Science Foundation
- Graduate Students
 - Mike Stokes, Greg Deese, Kadir Uslu, Ivan Gualtero
- Florida DOT
- Federal Highway Administration
- Air Logistics, CA
- Fyfe Company LLC